



User Chart



XS-310

Process	Description	Important Notes
Uses	Decks, Roof Decks, Concrete applications where a moisture barrier is needed	Similar to XS-350 with a slower set time
	Aids in leveling cracks and crevasses. Sagging can occur on vertical surfaces	Tip clogs easily typically during texturing
Techniques		
Composition	100% Polyurea	Mix Ratio by volume: 1A:1B Gel time: 10-12 sec
Temp Settings	Iso	140-160°F
	Resin	140-160°F
	Hose	130-150°F
Application	Sprayable Polyurethane	Coating thickness shall be min 60mil to gain physical properties on TDS. Moisture sensitive.
	E-XP1 / E-XP2	2100 PSI
	Fusion / P2	AR4242 (01) or smaller (always size mix module at <50% of proportioner output)
Equipment		
	E-10	130-150°F 1600 PSI; Frequency Dial #9
	Fusion / P2	AR2929 (00) or smaller (always size mix module at <50% of proportioner output)

**Please refer to the Technical Data Sheet for specific information regarding product performance.*

***Please refer to the Gun Manual for correct sizing of mix module to proportioner output.*

LINE-X Franchise Development Company
1862 Sparkman Drive · Huntsville, AL 35816 · 877-330-1331